



permanent



90 mic



decal label PP P 90

Super premium high gloss white coated polypropylene (PP) with 90 mic, with smooth surface. Offers high print quality, tear resistance, friction wear and resistance to damp and extreme environments.

SUBSTRATE

- White coated polypropylene (PP)

Finish	High Glossy		
	<i>Value</i>	<i>Tolerance</i>	<i>Standard</i>
Thickness (µm)	90	± 10%	GB/T6672
Weight (g/m ²)	108	± 10%	Digidelta Test Method
Opacity (%)	88		ISO 2471
Whiteness (CIE) (%)	90		GB 7974

ADHESIVE

- Clear acrylic based, permanent

	<i>Value</i>	<i>Standard</i>
Loop Tack steel (N/25 mm)	> 12	FINAT FTM 9
Loop Tack glass (N/25 mm)	> 16	FINAT FTM 9
Peel Adhesion steel 20 min (N/25 mm)	> 12	FINAT FTM 1
Peel Adhesion steel 24 h (N/25 mm)	> 14	FINAT FTM 1
Application temperature (°C)	> 10	
Service temperature (°C)	-10 a 70	
Certification	ISEGA - Food Safety	

LINER

- Glassine

	<i>Value</i>	<i>Tolerance</i>	<i>Standard</i>
Thickness (µm)	55	± 10%	ISO 534
Weight (g/m ²)	62	± 10%	ISO 536

decal label PP P 90

DURABILITY

- DURABILITY: < 1 year
- Shelf Life: 12 months from the date of manufacture, applicable only to material that has not been processed, and stored according to the following conditions:
- This material must be stored at a temperature of 20° C ± 5 ° C and 50% ± 5% relative humidity, without major climate deviations.
- The storage area must be dry and clean.
- Keep the material in the original package when not in use, in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.
- The product must be stored vertically, so that its quality is not compromised.

PRINTING METHODS

- Specially developed for water-based inkjet printing.
- An excessive quantity of ink in the product will result in changes in its characteristics, in inappropriate drying, lamination detachment and / or poor product performance.
- The suitability test between media, printer and inks is always recommended before use.

APPLICATION

- Application surface: not rough.
- Substrate not recommended for floor graphics (areas with car traffic); flexible or low energy substrates; non-flat surfaces; carton walls painted or unpainted; plaster walls; wallpaper; unclean or rough surfaces; surfaces with degraded paint.
- Printed materials must be dried properly before processing, such as laminating, varnishing or application.
- Do not expose to combustible vapors or spills.
- Surfaces on which the material will be applied must be carefully cleaned and free of dust or any other contamination that may affect the material adhesion.
- Non-vertical application results in a significant reduction in durability, as well as climate and angles of sun exposure. It is recommended that the material remains at least 24 hours at the temperature of the workplace before it is used.
- There may be other factors not described here that may influence the performance in the use.

IMPORTANT REMARKS

- Decal is not responsible for the ease or speed of removal of the applied material. It is necessary to have into account the appropriate air and substrate temperatures.
- The user must determine the material's compatibility with the intended specific application, before using it.
- We recommend that, to carry out a job, the same batch of product is used.
- The data provided in this information is based on our knowledge and experience. It is intended to be a source of information and is not a guarantee. It can be subject to change without previous notice.
- Decal is not responsible for misuse or improper storage, never being responsible for loss or damage to third parties.

Revision date of the technical data sheet: 21/10/24
Approved by: SC

Please, check our website www.decal-adhesive.com for additional information or request any clarification needed from our technicians